



Dry sliding wear behavior of aluminum based hybrid composites with graphite nanofiber–alumina fiber

J.S.S. Babu^{a,*}, C.G. Kang^{b,*}, H.H. Kim^c

^aEngineering Research Center (NSDM), Pusan National University, Busan, South Korea

^bSchool of Mechanical Engineering, Pusan National University, Busan, South Korea

^cDepartment of Precision and Mechanical Engineering, Pusan National University, Busan, South Korea

ARTICLE INFO

Article history:

Received 5 January 2011

Accepted 25 February 2011

Available online 3 March 2011

Keywords:

A. Composites–metal matrix

E. Wear

ABSTRACT

The wear behavior of aluminum based hybrid composites reinforced with graphite nanofiber (GNF) and alumina short fiber (Al_2O_{3sf}) in different volume fraction of fibers (10%, 15% and 20%) was studied under dry sliding conditions. The Taguchi approach to experimental design was used to identify those testing parameters that have the largest effects on wear loss and coefficient of friction of the composites. Sliding distance was found to be the prominent parameter affecting wear loss; applied load affected coefficient of friction most significantly. The results of Taguchi analysis indicate that wear loss increases with increasing load and sliding distance, but it is reduced with increasing sliding speed. Coefficient of friction decreases with increasing applied load and sliding speed whereas it increases with increasing sliding distance. The composites with 10 vol.% and 15 vol.% of fiber had the lowest wear loss and friction because of the mixture effect of GNFs and Al_2O_{3sf} . However, due to the effect of agglomerated GNFs, there was an increase in wear loss and friction at 20 vol.%.

© 2011 Elsevier Ltd. All rights reserved.

1. Introduction

In recent years, hybridization of reinforcements has gained significant importance in enhancing the properties of Metal matrix composites (MMCs) [1]. Moreover, mechanical properties of MMCs are improved by the reduced formation of intermetallic compounds at the interface between fibers and the matrix metal that results from the increase in interfacial area between fibers. Currently, aluminum matrix composites with micro–nano hybrid reinforcements are recognized as promising materials. The MMCs can show significantly lower wear rates than unreinforced alloys over wider ranges of load and sliding speeds. The wear resistances of MMCs have been found to be improved by hybridization with fibers, particles, whiskers and nanoparticles in different combinations [2]. Previously, a few studies on the wear behavior of hybrid MMCs have been reported. Ames and Alpas [3] studied on wear mechanisms in hybrid composites of graphite_p–SiC_p/A356 aluminum alloy. They highlighted that wear resistance was improved by hybridization. Zhang et al. [4] found a higher wear resistance for Al/(Al_2O_{3sf} + SiC_w) hybrid composites than for Al/SiC_w and Al/ Al_2O_{3sf} composites. Du and Li [5] studied the improvement on the wear properties of Al matrix by hybridization with the Al_2O_{3sf} /SiC_p system. Ahlatci et al. [6] investigated wear behaviors

of Al/(Al_2O_3p –SiC_p) hybrid composites produced by pressure infiltration. These composites, reinforced with 37 vol.% of Al_2O_3 and 25 vol.% of SiC particles also contained Mg up to 8%. Metal–metal and metal–abrasive wear resistance were found to increase with an increase in the Mg content. Tjong et al. [7] found out that the addition of BN into the Al/SiC_p composite system improved the wear resistance of the latter. Jun et al. [8] developed Al_2O_{3p} and carbon short fiber reinforced Al alloy (Al–Si–Cu–Mg–Ni) hybrid composites, by squeeze infiltrated route. Fiber normal-orientation was found to contribute to an improvement in the wear properties. Long et al. [9] highlighted that composites reinforced with a hybrid of SiC whisker, SiC particulate, and carbon fiber exhibited excellent wear resistance. Guo et al. [10] studied the tribological behavior of aluminum/graphite_p/SiC_p hybrid composites and found that the wear rate increased as the amount of graphite was increased up to a threshold value of 5%. Chen et al. [11] found a higher wear resistance for Cu/CNT composites than for pure Cu matrix, and that Ni–P–CNT electroless coating exhibited higher wear resistance and low coefficient than that of the Ni–graphite and Ni–P–SiC composites. Choi et al. [12] studied the wear behavior of aluminum based composites containing CNTs. They found that wear resistance is enhanced and the coefficient of friction is reduced. Kim et al. [13] observed that the incorporation of CNTs in the matrix resulted in a lower coefficient of friction and higher wear resistance.

It may be seen from the above discussions that the composites have been studied from different combinations of reinforcements

* Corresponding authors.

E-mail addresses: jssbabu@gmail.com (J.S.S. Babu), cgkang@pusan.ac.kr (C.G. Kang).